



VITEX THERM

Σύστημα Εξωτερικής Θερμομόνωσης
Thermal Insulation System

GRANIKOT LINEA

Acrylic Plaster

Very good quality acrylic plaster facade, weather-resistant and with great UV radiation properties. It has great adhesiveness, firmness and elasticity. Protects and decorates exterior and interior surfaces (plaster, concrete, facade thermal insulation systems). Certified with the CE marking according to EN 15824.

Advantages:

- Great resistance properties against weather and UV radiation
- Great adhesion, firmness and elasticity



PRODUCT FEATURES

TECHNICAL CHARACTERISTICS



Viscosity

50.000 – 66.000
cps (BROOKFIELD
sp.6/10rpm, 25°C)

Density

1,79 ± 0,05 Kg / L
(ISO 2811)

COLOR CARDS - FANDECKS



DILUTION



Water

0-2%

DRYING TIME



Touch dry

4-6 h

COLOURS

148

White and
selected
number
of shades
through
**Vitex Coloring
System**



CE MARKING



VITEX S.A. P.O. BOX 139 IMEROS TOPOS, ASPROPYRGOS GR 19300 GRANIKOT LINEA 23 DoP No : VIT-CPR-0021	
EN 15824 External render and internal plaster based on organic binders	
Reaction to fire	Euroclass B-s2,d0
Adhesion	≥ 0,5 MPa
Water absorption	W ₂
Water vapour permeability	V ₂
Thermal conductivity	1,09 W/m.K
Durability	≥ 0,9 MPa

PACKAGING

White	5 kg	25 kg
Bases	5 kg	25 kg



COVERAGE

Flat render:

- Granulometry 1,0 mm = 1,7-2,2 Kg/m²
- Granulometry 1,2 mm = 1,8-2,3 Kg/m²
- Granulometry 1,5 mm = 2,0-2,5 Kg/m²



VITEX THERM

Σύστημα Εξωτερικής Θερμομόνωσης
Thermal Insulation System

APPLICATION

APPLICATION FIELD

For the protection and decoration of exterior and interior surfaces (plaster, concrete, facade thermal insulation systems- ETICS)

PREPARATION



Surfaces must be smooth, clean and dry, free from grease, dust, loose or flaking paint.

To fill any cracks or holes use Acrylic Putty or Visto.

New surfaces made of plaster, concrete, cement, plasterboards or surfaces previously covered with emulsion or acrylic water-based paints need to be primed with Granikot Primer.



STEPS

1

Stir well with a mechanical drill, before application and at regular intervals during application. If required, dilute with maximum 2% of water.

2

Apply by stainless steel spatula and use a plastic trowel for forming the final texture.

3

Depending on the weather conditions, the structuring of the plaster should be done within 5 -15 minutes after applying the plaster in order to achieve the proper texture.

TIPS

- Application at 5-35°C and <80% RH. For exterior use, do not apply if there is a risk of rain/frost in the next 48 hours and strong wind conditions.
- The use of aggregates in the plaster may cause slight differences in shade compared to the fandeck. Thus, it is recommended for a uniform result either to use products from the same batch or to mix them if they are different.
- Weather conditions are particularly important for the quality and aesthetic effect of plaster so the application instructions

- should be strictly followed. Very high temperatures reduce the open time of the plaster, while rain on a fresh painted surface will cause deterioration of the final result.
- Avoid direct and uneven exposure to sun irradiation to prevent non-uniform drying.
 - In case structuring starts after 15 minutes of plaster application and the plaster has already begun drying, then the texture might become defective and uneven during the structuring.
 - It is dry to touch in 4-6 hours and in depth in 24 hours at +20°C and 65% relative

- humidity. Complete cure is achieved after about 14 days. These times vary depending on weather conditions (relative humidity and temperature).
- Tools must be cleaned immediately after use with water and if needed, with soapy water or detergent.
 - Recover unused material for re-use. After plaster application, seal the container and store it for future use.
 - Do not dispose of liquid waste into ground water table. Unused material requires special handling for safe disposal.

ADDITIONAL INFORMATION

VOCs (Volatile Organic Compounds)



"Exterior walls of mineral substrate".
VOC content limit **40 g/L**.
Maximum VOC content **39 g/L** VOCs
(ready for use product).

PRECAUTIONS



Please read carefully the labelling mentioned on the can before use. For detailed instructions on hazards and safety in use the Safety Data Sheet is available upon request.
Poisons Control Centre Tel. : +30 210 7793 777

STORAGE



5°C-38°C

Containers must be kept closed in a shady place away from direct sunlight, maximum 24 months from date of production.

The above technical data, information and instructions are based on our long experience and laboratory tests and are intended only to describe the product and determine its application. However, the end user should check the suitability of the product for its intended use. Our company guarantees the quality of the product itself, and in any case bears no responsibility for any damage or damage caused if the product is not used properly and in accordance with its instructions for use. The company has the right to revise this technical data sheet without any prior notice.

+30.210.5589.400
TECHNICAL SUPPORT



VITEX S.A., P.O. Box. 139 Imeros Topos, Aspropyrgos GR 193 00 | Tel. +30 210 5589500, Fax +30 210 4835007 | www.vitextherm.gr

Version: 05.2023 (This datasheet supersedes all previous versions)